

PRODUCT GROUPS

Solvent Free and High Solids

Epoxy Coatings Flowcoat SK Flowcoat SF41 Flowcoat TL Flowshield SL Peran ESD SL Peran STC Peran TCW

Water borne Epoxy Coatings Flowseal EPW Flowseal ESD EPW Peran WW

Solvent Free Epoxy Screeds

Flowtex Flowtex F1 Mortar Flowtex PT Mondéco Earth Peran STB

Polyurethane Screeds

Flowcrete HF Flowfresh HF Flowfresh ESD HF Flowfresh ESD MF Flowfresh MF/SL Flowfresh RT Mondéco TZ

Polyurethane Coatings

Flowseal LS (new) Flowseal UV Flowseal ESD UV

Flexible Polyurethane Coatings Deckshield Finish

Flowcoat LXP Flowgrip HD Flowprime LXP Flowshield LXP Flowshield LXP HD

Vinyl Ester Flowchem VE systems

Chemical resistant tests have been completed on the full range of Flowcrete Industrial Flooring products. Usually this has been effected upon products, which are pigmented, light grey in colour. All test pieces were cast as 20 x 20 x 4mm coupons (grouted and sealed where appropriate) being allowed to fully cure for 10 days at 20°C prior to being tested in accordance with the schedules described below.

The results detailed in the tables below should be considered as the most extreme circumstances as the test pieces were completely immersed in the test solutions. In practice, aggressive chemicals only come into contact with the uppermost working surface of any floor system, which significantly reduces the aggressive potential of a given chemical. Additionally, these effects should be minimised in practice by good house keeping and cleaning regimes.

In the absence of specific chemical contact data or combinations of chemicals listed below please contact our technical department or laboratories who will be pleased to advise you based upon experience from previous case histories. Alternatively, our technical centre can carry out further tests.

Note:

The data contained herein is based on laboratory tests performed under carefully controlled conditions. No warranty can be expressed or implied regarding the accuracy of this information, as it will apply to actual operational use. Plant operations vary widely, and the individual results obtained are affected by the specific conditions encountered, which are beyond our control.

Important:

We believe the information contained here to be true and accurate as of the date of publication. Flowcrete makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Please Note:

- Discoloration was not classified as chemical attack if hardness is unchanged.
- Higher temperatures will reduce the chemical resistance shown in the performance table.
- Some chemicals may concentrate due to evaporation and become more aggressive.
- Mixtures of chemicals can be more aggressive than might be expected from the individual components alone.
- Solvent resistant performances, in practice, are expected to exceed the values noted in the performance table due to good housekeeping combined with evaporation.
- The chemical resistance of Epoxy screed systems will be influenced by the integrity of the surface sealer - this being dependent upon service conditions and housekeeping.
- The assessment is based on a resin rich screed where permeation by liquid chemicals is minimal. The use of a highly filled screed will significantly reduce the chemical resistance shown in the performance table.

Rating	Description	Explanation
5	Excellent	No deleterious action after long term contact.
3	Medium Term	Unaffected after 1 month contact but may begin to fail thereafter.
1	Short Term	Unaffected after 24 hours contact but may begin to fail thereafter.
0	Not Resistant	Attacked on contact or within 2-3 hours

KEY: Chemical Resistance ratings are as follows: -

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

				1	Fest Result			
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Acetaldehyde		0	0	0	0	3	0	5
Acetic Acid @ 20°C	5	0	0	0	1	5	0	5
Acetic Acid @ 20°C	10	0	0	0	1	5	0	
Acetic Acid @ 60°C	10	0	0	0	0	0	0	5
Acetic Acid @ 20°C	20	0	0	0	0	5	0	5
Acetic Acid @ 20°C	30	0	0	0	0	4	0	5
Acetic Acid @ 60°C	30	0	0	0	0	0	0	5
Acetic Anhydride		0	0	0	0	5	0	5
Acetone		0	0	0	0	0	0	0
Acetonitrile		0	0	0	0	5	0	0
Acetyl Chloride		0	0	0	3	5	3	2
Acrolein		0	0	0	0	5	0	0
Acrylic acid @ 20°C		0	0	0	0	5	0	5
Acrylic Methyl Ester		0	0	0	3	5	3	5
Acrylonitrile		0	0	0	0	3	0	3
Adiponitrile		3	3	0	3	5	3	0
Allyl Alcohol		0	0	0	3	5	3	5
Allyl Chloride		0	0	0	3	5	3	5
Aluminium Sulphate @ 20°C	30	5	5	5	5	5	5	5
Amines		0	0	0	3	3	3	
Ammonia 0.880 @ 20°C		0	0	0	0	5	0	5
Ammonia (aq. Sol'n) @ 20°C	40	3	1	0	3	3	3	5
Ammonium chloride @ 20°C	30	5	5	5	5	5	5	5
Ammonium Nitrate @ 20°C	30	5	5	5	5	5	5	5
Amyl Acetate (Mixed Isomers)		3	3	3	3	5	3	5
Aniline		0	0	0	0	3	0	5
Aromasol H		5	5	3	5	5	5	3
Beer		5	5	5	5	5	5	5
Benzene		0	0	0	5	5	5	5
Benzyl Alcohol		0	0	0	0	5	0	5
Benzyl Chloride		0	0	0	0	5	0	
Blood		5	5	5	5	5	5	5
Boric Acid @ 20°C	20	3	3	0	3	5	3	5
Brine	30	5	5	5	5	5	5	5
Butanol		3	3	1	1	5	1	5
Butyl Acetate		3	3	1	3	5	3	5
Butyl Acrylate		5	5	3	3	5	3	5
Butyl Benzyl Phthalate		5	5	3	3	5	3	5
Butyl Ether		5	5	5	5	5	5	5
Butyric Acid		0	0	0	0	3	0	5
Butyrolactone		0	0	0	0	3	0	3
Calcium Carbonate sol'n	Sat'd	5	5	5	5	5	5	5

					Fest Result			
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Calcium Hydroxide susp'n	30	5	5	5	5	5	5	5
Caprolactam @ 20°C	20	3	3	3	5	5	5	5
Caprolactam @ 20°C	30	3	3	3	5	5	5	5
Caprolactam@ 20°C	50	3	3	3	5	5	5	5
Caprolactam @ 20°C	100	3	3	3	5	5	5	5
Carbon Tetrachloride		3	3	3	5	5	5	5
Castor Oil		5	5	5	5	5	5	5
Chicken Fats		3	5	0	3	5	3	5
Chloride of Lime sol'n @ 20°C	1	5	5	3	5	5	5	5
Chlorinated Paraffin		5	5	3	3	5	3	5
Chlorobenzene		0	0	0	0	3	0	5
Chloroform		0	0	0	0	0	0	5
Chromic acid @ 20°C	1	5	3	1	5	5	5	
Chromic acid @ 20°C	5	3	3	0	3	3	1	
Chromic acid @ 20°C	10	3	3	0	3	3	1	0
Chromic acid @ 20°C	30	1	1	0	3	3	1	0
Ciopen A30		5	5	3	5	5	5	5
Ciopen A60		5	5	3	5	5	5	5
Citric acid @ 20°C	10	5	5	3	5	5	5	5
Citric acid @ 20°C	30	5	5	3	5	5	5	5
Cleaning agent for heavy duty vehicles	10	3	3	0	0	5	0	5
Cleaning agent for heavy duty vehicles – concentrate		3	3	0	0	5	0	5
Cleaning petrol		5	5	5	5	5	5	5
Coconut fatty acid		5	5	5	5	5	5	5
Coconut oil		5	5	5	5	5	5	5
Cod liver oil		5	5	5	5	5	5	5
Common Salt sol'n @ 20°C	5	5	5	5	5	5	5	5
Common Salt sol'n	Sat'd	5	5	5	5	5	5	5
Copper Sulphate sol'n @ 20°C	30	5	5	5	5	5	5	5
Cotton Seed Oil		5	5	5	5	5	5	5
Creosote		5	5	3	3	5	3	
Cresylic acid		0	0	0	0	3	0	
Crotonaldehyde		0	0	0	0	3	0	
Crude Oil		5	5	5	5	5	5	5
Cyclohexane		5	5	5	5	5	5	5
Cyclohexanol		5	5	3	5	5	5	3
Cyclohexanone		0	0	0	5	5	5	
Decanol		5	5	5	5	5	5	5
Deionized water		5	5	5	5	5	5	5
Detergent solution	3	5	5	5	5	5	5	5
Diacetone alcohol		5	5	3	5	5	5	5

			-	7	Fest Result			
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Dibutyl phthalate		5	5	5	5	5	5	5
Dichlorobenzene		5	5	3	3	5	3	5
Dichloroethane		0	0	0	0	3	0	5
Dichloroethylene		0	0	0	0	5	0	5
Dichloromethane		0	0	0	0	5	0	
Dichloropropane		5	5	0	5	5	5	
Dicyclopentadiene		3	3	3	3	5	3	
Diesel oil		5	5	5	5	5	5	5
Diethanolamine		3	3	3	3	5	3	
Diethylamine (aq. Sol'n) @ 20°C	50	0	0	0	0	3	0	5
Diethylamine (aq. Sol'n) @ 20°C	60	0	0	0	0	0	0	5
Diethylene glycol		0	0	0	0	3	0	5
Diethylene glycol monobutyl ether		3	3	0	0	3	0	5
Diethylene glycol monoethyl ether		0	0	0	0	3	0	5
Diethylene glycol monomethyl ether		0	0	0	0	3	0	5
Diethylene triamine @ 20°C	100	0	0	0	0	4	4	
Diethylether		3	3	0	0	3	0	
Di-isobutyl ketone		5	5	3	3	5	3	0
Dimethylamine (aq.sol'n) @ 20°C	40	3	3	0	0	3	0	5
Dimethylamine (aq. Sol'n) @ 20°C	50	0	0	0	0	0	0	5
2-Diethylaminoethanol		3	3	1	3	3	3	
Dimethyl formamide (DMF)		0	0	0	0	0	0	5
Di-N-butyl phthalate		5	5	5	5	5	5	5
Di-octyl phthalate		5	5	5	5	5	5	5
Dioxane		0	0	0	3	5	3	5
Dipentene		5	5	3	5	5	5	5
Di-propylene glycol		5	5	5	5	5	5	5
Dishwashing detergent	3	5	5	5	5	5	5	5
Dutrex 217 UK		5	5	0	0	5	0	5
Electrocoating		5	5	0	5	5	5	5
Epichlorohydrin		0	0	0	3	5	3	5
Ethanol @ 20°C	10	5	5	5	5	5	5	5
Ethanol @ 20°C	15	5	5	5	5	5	5	5
Ethanol @ 20°C	70	5	5	3	5	5	5	5
Ethanol @ 20°C	96	3	3	0	5	5	3	5
Ethanolamine		0	0	0	3	3	3	5
Ethyl Acetate		0	0	0	5	5	5	5
Ethyl Acrylate		0	0	0	5	5	5	5
Ethyl Benzene		3	3	0	3	3	3	5
Ethylene Diamine		0	0	0	3	3	3	
Ethyl glycol		5	5	0	3	5	3	5
Ethylene glycol		5	5	5	5	5	5	5

					Fest Result		-	
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Ethyl glycol acetate		5	5	3	5	5	5	5
Ethylene Glycol Monobutyl ether		3	3	3	3	5	3	5
Ethylene Glycol monobutyl ether		5	5	3	3	5	3	
Ethylene glycol monoethyl ether		0	0	0	0	3	0	0
Ethylene glycol monoethyl ether		3	3	3	3	5	3	3
Ethylene glycol monomethyl ether		0	0	0	0	0	0	0
2-ethyl hexanol		5	5	3	3	5	3	3
2-ethyl hexyl acrylate		5	5	3	3	5	3	
Ethylene Amine		0	0	0	0	3	0	
Fish Oil		5	5	5	5	5	5	5
Formaldehyde @ 20°C	40	5	5	0	0	5	0	
Formaldehyde @ 20°C	100	3	3	0	0	5	0	5
Formic acid @ 20°C	5	3	3	0	0	5	0	5
Formic acid @ 20°C	10	3	3	0	0	5	0	5
Formic acid @ 20°C	20	0	0	0	0	5	0	5
Formic acid @ 20°C	30	0	0	0	0	5	0	5
Formic acid @ 20°C	98	0	0	0	0	3	0	5
Furfural		0	0	0	0	3	0	0
Furfuryl alcohol		0	0	0	0	3	0	5
Glycerol		5	5	5	5	5	5	5
Grape Juice		3	3	3	3	5	3	5
Groundnut oil		5	5	3	5	5	5	5
Heptane		5	5	3	5	5	5	
Hexane		5	5	3	5	5	5	5
Hexylene glycol		5	5	3	3	5	3	5
Hydrazine Hydrate		3	3	1	0	3	0	
Hydrochloric acid @ 20°C	5	5	5	3	0	5	0	5
Hydrochloric acid @ 20°C	10	3	3	0	0	5	0	5
Hydrochloric acid @ 20°C	36	0	0	0	0	3	0	5
Hydrofluoric acid @ 20°C	20	0	0	0	0	0	0	5
Hydrogen peroxide @ 20°C	3	5	5	3	5	5	5	5
Hydrogen peroxide @ 20°C	30	3	3	1	5	5	5	5
Hydrogen sulphide		3	3	0	3	5	3	5
Iso-amyl acetate		5	5	3	5	5	5	5
Iso-amyl alcohol		3	3	1	5	5	5	
Iso-butanol		3	3	1	5	5	5	5
Iso-butyl acetate		5	5	3	5	5	5	5
Iso-butyl aldehyde		0	0	0	3	3	3	
Iso-octanol		5	5	3	5	5	5	
Iso-pentane		5	5	3	5	5	5	
Iso-phorone		3	3	0	3	3	3	5

				1	Fest Result			
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Iso-phorone diamine @ 20°C		0	0	0	3	3	3	5
Isoprene		3	3	1	3	5	3	5
Iso-propanol		3	3	0	5	5	5	5
Jet Fuel		5	5	3	5	5	5	5
Kerosene		5	5	3	5	5	5	5
Lactic acid @ 20°C	2	5	5	3	5	5	5	5
Lactic acid @ 20°C	5	5	5	1	5	5	5	5
Lactic acid @ 20°C	30	3	3	0	3	5	3	5
Lactic acid @ 20°C	90	0	0	0	0	5	0	5
Lard		5	5	5	5	5	5	5
Lime Juice		3	3	0	3	5	3	5
Linseed fatty acid		5	5	5	5	5	5	5
Linseed oil		5	5	5	5	5	5	5
Maleic acid @ 20°C	30	5	5	3	5	5	5	5
Methanol		0	0	0	5	5	5	5
Methyl acetate		0	0	0	0	5	0	
Methyl acrylate		0	0	0	5	5	5	
Methylene chloride		0	0	0	0	0	0	0
Meta cresol		0	0	0	0	3	0	3
Methyl ethyl ketone (MEK)		0	0	0	0	0	0	5
Methyl glycol acetate		3	3	1	3	3	3	5
Methyl Isobutyl ketone (MIBK)		3	3	0	3	3	3	0
Methyl methacrylate		0	0	0	3	5	3	
N-methyl pyrollidone		0	0	0	0	0	0	
Milk		5	5	5	5	5	5	5
Mineral oil		5	5	5	5	5	5	5
Molasses		5	5	5	5	5	5	5
Morpholine		0	0	0	0	3	0	5
n-amino ethyl piperazine @ 20°C		0	0	0	3	3	3	4
Naphtha (petroleum)		5	5	3	3	5	3	5
Naphtha (solvent)		5	5	3	3	5	3	5
Naphthenic acid		5	5	5	5	5	5	
n-butanol		5	5	1	3	5	3	5
n-butyl acetate		5	5	1	3	5	3	5
n-heptanol		5	5	3	5	5	5	5
n-hexanol		5	5	3	5	5	5	5
Nitric acid @ 20°C	1	5	5	3	5	5	5	5
Nitric acid @ 20°C	3	5	5	0	5	5	5	5
Nitric acid @ 20°C	5	3	3	0	5	5	5	5
Nitric acid @ 20°C	10	3	3	0	5	5	5	5
Nitric acid @ 20°C	30	0	0	0	0	5	0	5
Nitric acid @ 20°C	69	0	0	0	0	0	0	0

					Fest Result			
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Nitrobenzene		0	0	0	0	0	0	5
Nitro-ethane		0	0	0	0	0	0	0
Nitro-propane (mixed isomers)		0	0	0	0	3	0	0
Nonanol		5	5	3	3	5	3	5
Nonyl phenol		5	5	3	5	5	5	5
n-pentane		5	5	3	5	5	5	5
Octanol		5	5	3	5	5	5	5
Oleic acid @ 20°C	100	3	3	0	5	5	5	5
Olive Oil		5	5	5	5	5	5	5
Ortho cresol		0	0	0	0	3	0	4
Orthophosphoric acid @ 20°C	85	0	0	0	3	5	3	5
Oxalic acid @ 20°C	2	5	5	3	3	5	3	5
Oxalic acid @ 20°C	10	3	3	0	5	5	5	5
Palm Kernel oil		5	5	5	5	5	5	5
Para cresol (aq)		0	0	0	0	3	0	0
Paraffin		5	5	5	5	5	5	5
Paraffin wax		5	5	5	5	5	5	5
Pentane (mixed isomers)		5	5	3	5	5	5	5
Perchlorethylene		3	3	1	5	5	5	5
Perchloric acid @ 20°C	30	3	3	0	3	4	3	5
Petrol		5	5	5	5	5	5	5
Petroleum ether		5	5	3	5	5	5	5
Phenol		0	0	0	0	0	0	5
Phosphoric acid @ 20°C	5	5	5	0	5	5	5	5
Phosphoric acid @ 20°C	10	5	5	0	5	5	5	5
Phosphoric acid @ 20°C	20	5	5	0	5	5	5	5
Phosphoric acid @ 20°C	50	5	5	0	5	5	5	5
Photographic developer sol'n	10	5	5	5	5	5	5	5
Pine oil		5	5	5	5	5	5	5
Polypropylene glycol		5	5	5	5	5	5	5
Potassium dichromate @ 20°C	20	5	5	3	3	5	3	5
Potassium hydroxide sol'n @ 20°C	5	5	5	5	5	5	5	5
Potassium hydroxide sol'n @ 20°C	10	5	5	5	5	5	5	5
Potassium hydroxide sol'n @ 100°C	10	5	5	5	5	5	5	5
Potassium hydroxide sol'n @ 20°C	20	5	5	5	5	5	5	5
Potassium hydroxide sol'n @ 20°C	50	5	5	5	5	5	5	5
Pyridine		0	0	0	3	3	3	
Pyridine bases		0	0	0	3	3	3	
Seawater		5	5	5	5	5	5	5
Sec-butanol		5	5	3	3	5	3	5
Shell Rotella oil		5	5	5	5	5	5	5
Shellsol A		5	5	3	3	5	3	5

				7	Fest Result			
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Shellsol T		5	5	3	3	5	3	
Silicone oil		5	5	5	5	5	5	5
Skydrol A500		5	5	0	5	5	5	5
Soap solution		5	5	5	5	5	5	5
Soda solution (saturated)		5	5	5	5	5	5	5
Soda solution (dilute)		5	5	5	5	5	5	5
Sodium Chloride (sat'd sol'n)		5	5	5	5	5	5	5
Sodium dichromate aq. Sol'n @ 20°C	33	5	5	3	3	5	3	5
Sodium bicarbonate (aq)		5	5	5	5	5	5	5
Sodium hydroxide @ 20°C	5	5	5	5	5	5	5	5
Sodium hydroxide @ 20°C	20	5	5	5	5	5	5	5
Sodium hydroxide @ 20°C	50	5	5	5	5	5	5	5
Sodium hydroxide @ 60°C	50	0	0	0	0	0	0	5
Sodium hypochlorite sol'n 15% available CI @ 20°C		5	5	1	5	5	3	5
Sodium nitrate @ 20°C	20	5	5	5	5	5	5	
Solvesso 150		5	5	3	3	5	3	5
Soya bean oil		5	5	5	5	5	5	5
Stannic chloride		5	5	3	5	5	5	5
Styrene		3	3	0	3	5	3	5
Succinic acid	10	5	5	0	0	5	0	5
Sugar solution @ 20°C	30	5	5	5	5	5	5	5
Sulphuric acid @ 20°C	5	5	5	0	3	5	3	5
Sulphuric acid @ 20°C	10	5	5	0	3	5	3	5
Sulphuric acid @ 100°C	10	0	0	0	0	0	0	5
Sulphuric acid @ 20°C	20	5	5	0	0	5	0	5
Sulphuric acid @ 20°C	30	3	3	0	0	3	0	5
Sulphuric acid @ 20°C	50	3	3	0	0	3	0	5
Sulphuric acid @ 20°C	98	0	0	0	0	0	0	0
Sunflower seed oil		5	5	5	5	5	5	5
Tall oil		5	5	5	5	5	5	5
Tall oil fatty acid		5	5	5	5	5	5	5
Tallow		5	5	5	5	5	5	
Tapwater		5	5	5	5	5	5	
Tartaric acid @ 20°C	5	5	5	0	5	5	5	5
Tartar solution @ 20°C	5	5	5	0	0	5	0	5
Teepol		5	5	3	5	5	5	5
Tert-butanol		5	5	3	3	5	3	5
Tetrachloroethylene		5	5	0	3	5	3	5
Tetrahydrofuran (THF)		0	0	0	0	3	0	
Tetrahydronaphthalene		5	5	0	3	5	3	
Titanium tetrachloride		3	3	0	3	3	3	

				٦	Fest Result			
Chemical	%	Solvent Free Epoxy Coating	Solvent Free Epoxy Screed	Water born epoxy coating	Polyure- thane Coating	Polyure- thane Screed	Flexible Polyure- thane Coatings	Vinyl Ester
Toluene		0	0	0	1	1	0	5
Toluene-di-isocyanate		5	5	3	5	5	5	5
Tributyl citrate		5	5	3	5	5	5	5
1,1,1 – trichloroethane		5	5	0	0	5	0	5
Trichloroethylene		0	0	0	0	0	0	5
Tri cresyl phosphate		5	5	5	5	5	5	5
Triethanolamine		5	5	0	3	5	3	5
Triethylene glycol		5	5	3	5	5	5	5
Triethylene cetramine		0	0	0	3	5	3	5
Triolyl phosphate		5	5	5	5	5	5	5
Trixylyl phosphate		5	5	5	5	5	5	5
Urea @ 20°C	30	5	5	5	5	5	5	5
Vegetable Juice		5	5	5	5	5	5	5
Water @ 20°C		5	5	5	5	5	5	5
Water, distilled @ 100°C		5	5	5	5	5	5	5
Whisky		3	3	1	5	5	5	5
White Spirit		5	5	5	5	5	5	5
Wine		3	3	1	5	5	5	5
Xylene (mixed Isomers)		3	3	1	5	5	1	5

Page 8 of 8